

**Amendments to the Claims:**

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A laminated and molded body obtained by coextruding and molding at least two kinds of resin materials, ~~characterized in wherein~~

~~that~~ at least one layer of said laminated and molded body comprises a colored layer having a thickness continuously ~~or intermittently~~ varied in a predetermined direction with respect to the extruding direction of the resin material of said colored layer and the full thickness of said laminated and molded body is substantially constant along said predetermined direction.

2. (Currently Amended) The laminated and molded body of claim 1, ~~characterized in wherein~~

~~that~~ the predetermined direction is a direction parallel to the extruding direction of said at least one layer of said laminated and molded body.

3. (Currently Amended) The laminated and molded body of claim 1, ~~characterized in wherein~~

~~that~~ the predetermined direction is a direction intersecting the extruding direction of said at least one layer of said laminated and molded body.

4. (Currently Amended) The laminated and molded body of claim 1, ~~characterized in wherein~~

~~that~~ the predetermined direction comprises a direction parallel to the extruding direction of said at least one layer of said laminated and molded body and another direction intersecting the extruding direction.

5. (Canceled)

6. (Currently Amended) The laminated and molded body of claim 1, ~~characterized in~~wherein  
~~that~~ said colored layer has a thickness varied within a range of 50% of the full thickness of said laminated and molded body.

7. (Currently Amended) The laminated and molded body claim 1, ~~characterized in~~wherein  
~~that~~ said laminated and molded body is a blow-molding aimed preform, a direct-blow molded bottle, a tube, or a blow molded tube.

8. (Withdrawn-Currently Amended) A manufacturing method of ~~a~~forming the laminated and molded body ~~to be formed of claim 1~~ by coextruding at least two kinds of resin materials, ~~characterized in~~

~~that the~~ said method ~~comprises the steps of~~comprising:  
extruding a colored layer as at least one layer of said laminated and molded ~~body,~~  
~~and~~body from a first kind of resin material; and  
controlling an extruding amount of the resin material of said colored layer such that said colored layer has a thickness continuously ~~or intermittently~~ varied in a predetermined direction with respect to the extruding direction of the resin material of said colored ~~layer~~layer; and  
controlling an extruding amount of a second kind of resin material forming at least one layer other than said colored layer such that the full thickness of said laminated and molded body is substantially constant along said predetermined direction.

9. (Withdrawn-Currently Amended) The manufacturing method of claim 8, ~~characterized in~~wherein  
~~that~~ the predetermined direction is a direction parallel to the extruding direction of said at least one layer of said laminated and molded body.

10. (Withdrawn-Currently Amended) The manufacturing method of claim 8,  
~~characterized in~~wherein

~~that~~ the predetermined direction is a direction intersecting the extruding direction of  
said at least one layer of said laminated and molded body.

11. (Withdrawn-Currently Amended) The manufacturing method of claim 8,  
~~characterized in~~wherein

~~that~~ the predetermined direction comprises a direction parallel to the extruding  
direction of said at least one layer of said laminated and molded body and another direction  
intersecting the extruding direction.

12. (Canceled)

13. (Withdrawn-Currently Amended) The manufacturing method of claim 8,  
~~characterized in~~

~~that~~ said manufacturing method further ~~comprises the step of~~comprising:

controlling the extruding amount of the resin material of said colored layer such that  
said colored layer has a thickness varied within a range of 50% of the full thickness of said  
laminated and molded body.

14. (Withdrawn-Currently Amended) The manufacturing method of claim 8,  
~~characterized in~~wherein

~~that~~ said laminated and molded body forms a blow-molding aimed preform, a direct-  
blow molded bottle, a tube, or a blow molded tube.